



An adhesive polyethylene stretch film which is obtained by a simultaneous process of four different pre-laminated layers. Stretchable to approx 150% it can be used on both half automatic and fully-automatic power-stretch machines. Suitable for loads of any size or shape, it comes also with an anti-UV treatment to resolve problems which may arise with loads stored out door.



TECHNICAL INFORMATIONS

PROPERTIES		STANDARD	MEASURE UNIT	VALUE
BREAKING STRENGTH	LONG	ASTM D 882	KG mm ²	4
	TRASV			2,4
ELONGATION STRENGTH	LONG	ASTM D 882	%	500
	TRASV			750
TEAR STRENGTH	LONG	ASTM D 1922	Gr.	100
	TRASV			200
PUNCTURE STRENGTH		DERIBLOK'S OWN NORMS	Gr.	1500
DART TEST		ASTM D 1709	Gr.	100
GLOSS		ASTM D 2457	%	91
SLIP		ASTM D 1894	-	> 1

